

Tower Oil & Technology Co.

RUSTBEAT® A Family of Rust Preventives

TOWER RUSTBEAT 2 – Excellent outdoor rust preventive. Solvent type. Compatible with most metalworking fluids and need not be removed before further machining. Excellent penetration on bundled bars and flats.

Flash Point 108°F
Type of Film (Class I) Dry, Waxy
Application Brush, Dip or Swab
Protection Approx. 1 year outdoors
Drying Time One Hour
Coverage (per gallon) Approx. 900 sq. ft.
Removal Solvents or Vapor Degreaser

TOWER RUSTBEAT 1313 – Designed as a heavy duty rust preventive for indoor storage and long distance transit. Excellent for cold drawn bar and wire.

Viscosity S.U.S. @ 100°F 110-125
Flash Point 310-330°F
Type of Film (Class III) Oily
Application Spray, Dip, Brush or Swab
Protection Approx. 1 year indoors
Drying Time Does not dry
Coverage (per gallon) Approx. 900 sq. ft.
Removal Easily removed by any conventional cleaning method.

TOWER RUSTBEAT 605A – Formulated specifically to resist rust under conditions of high humidity and frequent temperature changes. Used as a die lubricant on metal forming operations.

Viscosity S.U.S. @ 100°F 50-85
Flash Point 290°F
Type of Film (Class III) Oily
Application Spray, Dip or Roll Coater
Protection Approx. 9 months indoors
Drying Time Does not dry
Coverage (per gallon) Approx. 1,000 sq. ft.
Removal Easily removed by any conventional cleaning method.

TOWER RUSTBEAT 198 – Especially compounded to displace residue from alkaline cleaners. Also water displacing. Will not stain flat stacked parts. Leaves clean dry thin film.

Flash Point Minimum 105°F
Type of Film (Class I) Dry
Application Spray, Brush or Dip
Protection Approx. 9 months indoors
Coverage (per gallon) 1,200 sq. ft.
Removal Solvents or Vapor Degreaser

TOWER RUSTBEAT SD-26 – Displaces water and water soluble lubricants and simultaneously deposits a corrosion preventive film on metal surfaces.

Viscosity S.U.S. @ 100°F 45-50
Flash Point Minimum 230°F
Type of Film Very light oil
Application Spray, Flood or Dip
Protection Approx. 6 months indoors
Drying Time Does not dry
Coverage (per gallon) 1,200 sq. ft.
Cleaning Easily removed by any conventional method.

TOWER RUSTBEAT WS-72 – Water soluble rust preventive for indoor use. Has excellent compatibility with lubricating and metalworking oils.

Flash Point (Concentrate) 310-330°F
Type of Film Oily
Dilution (water to concentrate) 5:1 - 10:1
Application Spray, Dip, Brush or Swab
Protection Approx. 6-12 months indoors
Drying Time Does not dry
Coverage (per gallon) 6,000-12,000 sq. ft.
Removal Easily removed by any conventional method.

TECHICAL SUPPORT

TOWER wants to assist you in evaluation and selection of suitable products. We urge you to take advantage of this service. This information sheet and **TOWER's** assistance, however, are not a substitute for your own testing and evaluation.

99264