



TOWERKOTE 59-P

TOWERKOTE 59-P is an IRON PHOSPHATE CONVERSION COATING, consisting of a blend of acid salts and accelerators for phosphate coating of ferrous and non-ferrous surfaces in recirculating and soak applications. **TOWERKOTE 59-P** leaves a dense grey colored phosphate coating with a coating weight averaging between 5 to 50 milligrams per square foot.

USAGE

For recirculating spray washers, use **TOWERKOTE 59-P** at 2 to 10% concentration by volume at 100 to 150°F for one to two minutes of contact time.

For dip tanks, **TOWERKOTE 59-P** should be used at 5 to 7% concentration by volume at 100 to 150°F, for three to five minutes contact time.

WARNING: **TOWERKOTE 59-P** contains acid phosphate salts which can cause irritation. Avoid contact with eyes, skin and clothing. See Material Safety Date for further safety precautions.

PHYSICAL CHARACTERISTICS

Density	1.21g/ml 10.1 lbs/gal
Appearance	Clear Liquid
Odor	Bland
pH (3% solution)	Typically 3 to 5

TECHNICAL SUPPORT

TOWER wants to assist you in evaluation and selection of suitable products. We urge you to take advantage of this service. This information sheet and **TOWER's** assistance, however, are not a substitute for your own testing and evaluation.

04226